

BONDEX**TECHNICAL DATA SHEET****34000****1. Product Description**

- 1.1 Trade Name : **BONDEX Regatta Yacht Varnish**
- 1.2 Quality No. : **34000**
- 1.3 Type : Yacht varnish for treatment of wooden boats out- and inboard, when a glossy, solid, and waterproof surface is required
- 1.4 Manufacturer : Dyrup A/S - Gladsaxevej 300 - 2860 Søborg - Denmark
- 1.5 Where to use : Wooden boats.
- 1.6 Form Supplied : Ready for use.
- 1.7 Colour Range : Colourless
- 1.8 Can Sizes : 0.75 L - 2.50 L

2. Composition

- 2.1 Binder : Oil modified alkyd resin.
- 2.2 Solvents : White spirit.

3. Technical Data

- 3.1 Specific Gravity : App. 0.9 kg/litre.
- 3.2 Viscosity : H-K (Gardner-holdt).
- 3.3 Solid Content : App. 53,0 WW%.
- 3.4 Gloss : High-gloss, more than 90 at a 60° angle.
- 3.5 Special Qualities : Resistance towards influence from sea water, sun, and wind. Resistance towards common cleaning materials.
- 3.6 Coverage : 10-14 m²/l.
- 3.8 Drying Time : Recoatable: 4 hours.
- 3.9 Storage : Firmly closed and frost-free.
- 3.10 VOC : EU limit value for this product (cat. A/e): 500 g/l (200). This product contains max 450 g/l VOC.

4. Substrate & Preparation

- 4.1 Substrate : The substrate must be dry, clean, and solid.
- 4.2 Pre-treatment : The most durable result is achieved by priming with a BONDEX primer.
- 4.3 Application : New wood : 2-3 coats of BONDEX Regatta Yacht Varnish.
Previously varnished wood : Slight sanding, wet or dry. Detached spots should be treated with a BONDEX primer.

BONDEX**TECHNICAL DATA SHEET****34000**

- 4.3 Application : Worn-down, discoloured wood : Plane, scratch or sand until sound wood. Do not use at temperatures below 5°C or above 80% relative humidity, based on a daily average.
- 4.6 Thinning : Do not thin.
- 4.7 Cleaning of Tools : White spirit.

5. Safety Precautions

- 5.1 In General : Common safety rules for work with paints must be observed. Further information is available from our Material Safety Data Sheet.

This Technical Data Sheet is assigned to describe the applicability of BONDEX Regatta Yacht Varnish in a serious and non-binding way. The technical indications are based on years of research, but the consumer is hereby not dissuaded to test the purpose of BONDEX Regatta Yacht Varnish before use. If any doubts, please apply to our agents or technical departments. This Technical Data Sheet replaces all former editions.